


## **Technical data sheet**

## Article number: 594-41104

## **TAG132LA4**

Self-laminating labels, laser printer



**Product Group** 

Product Family	Helatag 1104 (White-Transparent)
Material	Type 1104, Polyester, white transparent, self-laminating (1104)
Colour	White (WH), Transparent (CL)
Adhesive	Acrylic
Adhesive strength	Stainless steel: 440-465 N/m (FTM 1), Acrylates: 550-595 N/m (FTM 1), Glass: 410-445 N/m (FTM 1)
Application Method	The functionality and durability of the labels can be negatively affected if improperly processed or applied. All surfaces to be bonded must be clean, dry as well as free from dust and grease. Avoid touching the adhesive surface of the label as this could impair the application performance.
Bundle Diameter max (metric)	7.60 mm
Bundle Ø min.	3.80 mm
Curing Temperature	from +10 °C
Flammability	UL 94 V0
Height (H)	12.70 mm
Height (H2)	36.50 mm
Initial tack [Test method]	280 g/cm² [ASTM D2979]
Labels per Row	9 pcs.
Labels per Sheet	63 pcs.
Operating Temperature	-40 °C to +150 °C
Peel strength [Test method]	100 h [FINAT FTM 8]
Self adhesive (Yes/No)	Yes
Storage conditions	50% relative humidity., The storage in the original packaging is recommended., Please avoid warehousing under impacts such as high humidity, heat and coldness.
Thickness of Adhesive (TA) nom.	21.5 μm
Thickness of Foil [Test method]	25 μm [ASTM D3652]
UL-File Number	MH61377



Width (W)	20.32 mm
Width of Liner (WL)	210.00 mm





Ped on 7. August 202