INCH-POUND

MIL-DTL-83723/16B w/AMENDMENT 2 16 May 2011 SUPERSEDING MIL-C-83723/16B(USAF) AMENDMENT 1 14 September 1993

DETAIL SPECIFICATION SHEET

CONNECTOR, ELECTRICAL, BACKSHELL, WITH HEAT-SHRINKABLE STRAIN-RELIEF, BOOT (STRAIGHT OR RIGHT ANGLE), BAYONET-COUPLING, SERIES I AND III

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-83723.





FIGURE 1. Completed assembly.

AMSC N/A FSC 5935



| Inches | mm |
|--------|------|
| .025 | 0.64 |
| .035 | 0.89 |
| .041 | 1.04 |
| .051 | 1.30 |
| .070 | 1.78 |
| .090 | 2.29 |
| .125 | 3.18 |
| .139 | 3.35 |
| .145 | 3.68 |
| .282 | 7.16 |
| .304 | 7.72 |
| | |

FIGURE 2. Backshell, bayonet coupling.

| | Dimensions in inches | | | | | | | | | Р |
|-------|----------------------|----------|----------|----------|----------|----------|----------|----------|------------------|-------|
| Shell | Α | В | С | D | E | F | G | Н | V | No. |
| size | Dia | Dia | Dia | Dia | Dia | | Dia | Dia | Threads | of |
| | (Max) | (Min) | (Max) | (Min) | (Min) | (Max) | (Min) | (Max) | | Teeth |
| 8 | .657 | .500 | .360 | .299 | .250 | .540 | .668 | .600 | .500-20UNF-2B | 12 |
| | (16.687) | (12.7) | (9.144) | (7.594) | (6.35) | (13.716) | (16.967) | (15.24) | | |
| 10 | .774 | .625 | .494 | .433 | .295 | .540 | .783 | .715 | .625-24UNEF-2B | 15 |
| | (19.659) | (15.875) | (12.547) | (10.998) | (7.493) | (13.716) | (19.888) | (18.161) | | |
| 12 | .898 | .750 | .610 | .549 | .491 | .540 | .918 | .850 | .750-20UNEF-2B | 21 |
| | (22.809) | (19.05) | (15.494) | (13.944) | (12.471) | (13.716) | (23.317) | (21.29) | | |
| 14 | 1.024 | .875 | .735 | .674 | .555 | .540 | 1.043 | .975 | .875-20UNEF-2B | 24 |
| | (26.009) | (22.225) | (18.669) | (17.119) | (14.097) | (13.716) | (26.492) | (24.765) | | |
| 16 | 1.152 | 1.000 | .860 | .799 | .680 | .540 | 1.218 | 1.100 | 1.000-20UNEF-2B | 30 |
| | (22.260) | (25.4) | (21.844) | (20.294) | (9.652) | (13.716) | (30.937) | (27.94) | | |
| 18 | 1.243 | 1.062 | .916 | .869 | .759 | .540 | 1.290 | 1.172 | 1.0625-18UNEF-2B | 33 |
| | (31.572) | (26.974) | (23.266) | (22.072) | (19.278) | (13.716) | (32.766) | (29.768) | | |
| 20 | 1.370 | 1.188 | 1.041 | .994 | .884 | .540 | 1.416 | 1.298 | 1.1875-18UNEF-2B | 36 |
| | (34.798) | (30.175) | (26.441) | (25.247) | (22.453) | (13.716) | (35.966) | (32.967) | | |
| 22 | 1.443 | 1.312 | 1.166 | 1.119 | 1.009 | .540 | 1.540 | 1.422 | 1.3125-18UNEF-2B | 39 |
| | (36.652) | (33.324) | (29.166) | (28.422) | (25.628) | (13.716) | (39.116) | (36.118) | | |
| 24 | 1.618 | 1.438 | 1.291 | 1.244 | 1.134 | .540 | 1.666 | 1.548 | 1.4375-18UNEF-2B | 42 or |
| | (41.097) | (36.525) | (32.791) | (31.597) | (28.803) | (13.716) | (42.316) | (39.319) | | 45 |

NOTES:

- 1. Material: Aluminum alloy.
- 2. Finish: Class R, 200°C, conductive finish.
- 3. Dimensions apply after plating.
- 4. Remove all burrs and sharp edges.
- 5. Complete backshell consists of accessory nut and a follower. Accessory nut shall be captivated to, and shall be free to rotate on, the follower.
- 6. Dimensions are in inches. Metric equivalents are given for information only.

FIGURE 2. <u>Backshell</u>, <u>bayonet coupling</u> – Continued.





FIGURE 3. Heat shrinkable strain relief boot, straight.

| | | | | [| inches | | | | |
|-------|----------|-----------|-------------------|----------|-----------|-----------|-----------|-----------|-----------|
| Shell | Н | Dia | | J Dia | | Р | R | S | Т |
| size | As | | As Supplied | | | | | | |
| | Supplied | Recovered | (N | lin) | Recovered | Recovered | Recovered | Recovered | Recovered |
| | (Min) | (Max) | (No | te 2) | (Max) | | | | |
| | | | Material Material | | | | | | |
| | | | type A | type B | | | | | |
| 8 | 1.01 | .59 | 1.01 | .63 | .29 | 4.77 | .48 | .59 | .040 |
| | (25.64) | (14.966) | (25.654) | (16.002) | (7.336) | (121.158) | (12.192) | (14.986) | (1.016) |
| 10 | 1.16 | .74 | 1.16 | .72 | .33 | 5.46 | .48 | .60 | .040 |
| | (29.48) | (18.796) | (29.464) | (18.288) | (8.382) | (138.684) | (12.192) | (15.24) | (1.016) |
| 12 | 1.34 | .90 | 1.34 | .84 | 38 | 6.28 | .48 | .62 | .040 |
| | (34.03) | (22.86) | (34.036) | (21.336) | (9.652) | (159.512) | (12.192) | (15.748) | (1.016) |
| 14 | 1.34 | .90 | 1.34 | .84 | 38 | 6.28 | .48 | .62 | .040 |
| | (34.03) | (22.86) | (34.036) | (21.336) | (9.652) | (159.512) | (12.192) | (15.748) | (1.016) |
| 16 | 1.47 | 1.16 | 1.47 | .91 | .41 | 7.00 | .55 | .70 | .065 |
| | (37.338) | (29.464) | (37.338) | (23.114) | (10.414) | (177.8) | (13.97) | (17.78) | (1.651) |
| 18 | 1.47 | 1.16 | 1.47 | .91 | .41 | 7.00 | .55 | .70 | .065 |
| | (37.338) | (29.464) | (37.338) | (23.114) | (10.414) | (177.8) | (13.97) | (17.78) | (1.651) |
| 20 | 1.72 | 1.34 | 1.72 | 1.07 | .48 | 8.00 | .60 | .78 | .065 |
| | (43.688) | (34.06) | (43.688) | (27.178) | (12.192) | (203.2) | (15.24) | (19.812) | (1.651) |
| 22 | 1.72 | 1.34 | 1.72 | 1.07 | .48 | 8.00 | .60 | .78 | .065 |
| | (43.668) | (34.06) | (43.688) | (27.178) | (12.192) | (203.2) | (15.24) | (19.812) | (1.651) |
| 24 | 1.97 | 1.62 | 1.97 | 1.23 | .56 | 8.00 | .60 | .82 | .065 |
| | (50.03) | (41.148) | (50.30) | (31.242) | (14.224) | (203.2) | (15.24) | (20.828) | (1.651) |

NOTES:

- 1. Boots will shrink to recovered dimensions upon application of heat in excess of 175°C.
- 2. Material shall be modified crosslinked polyolefin (Type A: 150°C) or fluoroelastomer (Type B: 200°C) and shall have the characteristics shown in table I.
 - A. Polyolefin.
 - B. Fluoroelastomer.
- 3. Dimensions are in inches. Metric equivalents are given for information only.

FIGURE 3. Heat shrinkable strain relief boot, straight - Continued.



| | Dimensions in inches | | | | | | | | |
|-------|----------------------|-----------|-------------------|----------|-----------|-----------|-----------|-----------|-----------|
| Shell | Н | Dia | | J Dia | | Р | R | S | Т |
| size | As | | As Supplied | | | | | | |
| | Supplied | Recovered | | in) | Recovered | Recovered | Recovered | Recovered | Recovered |
| | (min) | (max) | (Not | te 2) | (max) | | | | |
| | | | Material Material | | | | | | |
| | | | type A | type B | | | | | |
| 8 | 1.01 | .59 | 1.01 | .63 | .29 | 4.88 | .78 | .59 | .040 |
| | (25.654) | (14.986) | (25.654) | (16.002) | (7.366) | (123.952) | (19.812) | (14.986) | (1.625) |
| 10 | 1.16 | .74 | 1.16 | .72 | .33 | 5.76 | .82 | .60 | .040 |
| | (29.464) | (18.796) | (29.464) | (18.288) | (8.382) | (146.304) | (20.828) | (15.24) | (1.625) |
| 12 | 1.34 | .90 | 1.34 | .84 | .38 | 6.78 | .86 | .62 | .040 |
| | (34.036) | (22.86) | (34.036) | (21.336) | (9.652) | (172.212) | (21.844) | (15.748) | (1.625) |
| 14 | 1.34 | .90 | 1.34 | .84 | .38 | 6.78 | .86 | .62 | .040 |
| | (34.036) | (22.86) | (34.036) | (21.336) | (9.652) | (172.212) | (21.844) | (15.748) | (1.625) |
| 16 | 1.47 | 1.16 | 1.47 | .91 | .41 | 7.29 | .96 | .70 | .065 |
| | (37.338) | (29.464) | (37.338) | (23.114) | (10.414) | (185.166) | (24.384) | (17.78) | (1.625) |
| 18 | 1.47 | 1.16 | 1.47 | .91 | .41 | 7.29 | .96 | .70 | .065 |
| | (37.338) | (29.464) | (37.338) | (23.114) | (10.414) | (185.166) | (24.384) | (17.78) | (1.625) |
| 20 | 1.72 | 1.34 | 1.72 | 1.07 | .48 | 8.41 | 1.08 | .78 | .065 |
| | (43.688) | (34.036) | (43.688) | (27.178) | (12.192) | (213.614) | (27.432) | (19.812) | (1.625) |
| 22 | 1.72 | 1.34 | 1.72 | 1.07 | .48 | 8.41 | 1.08 | .78 | .065 |
| | (43.688) | (34.036) | (43.688) | (27.178) | (12.192) | (213.614) | (27.432) | (19.812) | (1.625) |
| 24 | 1.97 | 1.62 | 1.97 | 1.23 | .56 | 8.84 | 1.16 | .82 | .065 |
| | (50.038) | (41.148) | (50.038) | (31.242) | (14.224) | (224.536) | (29.464) | (20.828) | (1.625) |

NOTES:

- 1. Boots will shrink to recovered dimensions upon application of heat in excess of 175°C.
- 2. Material shall be modified crosslinked polyolefin (Type A: 150°C) or fluoroelastomer (Type B: 200°C) and shall have the characteristics shown in table I.
 - A. Polyolefin.
 - B. Fluoroelastomer.
- 3. Dimensions are in inches. Metric equivalents are given for information only.

FIGURE 4. Heat shrinkable strain boot, right angle (90°).

REQUIREMENTS:

Dimensions and configurations: See figures 1 through 4.

Material: Backshell - See figure 2. Heat shrinkable boots - see figures 3 and 4 and table I.

QUALIFICATION:

Initial qualification shall consist of the entire list of material requirements in table I and the performance test for temperature life on figure 5. Sampling for initial qualification shall be in accordance with MIL-DTL-83723.

1. Elastic memory:

A 6 x 1/8-inch specimen cut from a molded slab shall be marked with two parallel gage lines 1 inch apart in the central portion of the specimen. A 2-inch portion of the specimen including both gage lines then shall be heated for 5 minutes in a $200 \pm 5^{\circ}$ C ($392 \pm 9^{\circ}$ F) oven or equivalent, removed from the oven, and stretched within 10 seconds until the gage lines are 4 inches apart. The extended specimen then shall be cooled at room temperature and released from tension. After 24 hours at room temperature, the distance between the gage lines shall be measured and recorded as the extended length. The portion of the specimen including both gage lines then shall be reheated for 5 minutes in a $200 \pm 5^{\circ}$ C ($392 \pm 9^{\circ}$ F) oven or equivalent, removed from the oven, and allowed to retract. The specimen shall again be cooled to room temperature and the distance between the gage lines then shall be measured and recorded as the retracted length. Expansion and retraction shall be calculated as follows:

Expansion = (extended length -1) x 100 percent

Retraction = extended length - retracted length x 100 percent

2. Low-temperature flexibility:

A 6 x 1/4-inch specimen cut from a molded slab shall be mounted in a loop position between movable, parallel jaws 2-1/2 inches apart. Each end of the specimen shall be firmly fastened by at least 3/4 of an inch extending into a set of jaws. The specimen and the test fixture shall be conditioned for 4 hours at -55° \pm 2°C (-67 \pm 4°F). While at this temperature, the jaws shall be moved rapidly from 2 ½ inch to a 1-inch separation.

3. Heat shock:

A 6-inch by 1/4-inch specimen cut from a molded slab shall be conditioned in an oven at temperature. After this conditioning, the specimen shall be visually examined for evidence of dripping, flowing, or cracking.

4. Heat aging:

Three specimens, prepared and measured in accordance with ASTM-D412, shall be conditioned at temperature for 168 hours in an oven with an air velocity of from 100 to 200 feet per minute past the specimens. After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and tested for tensile strength and elongation.

5. Fluid resistance:

Specimens, $6 \times 0.25 \times 0.075$ shall be cut from molded slabs. Three (3) specimens shall be immersed in each of the fluids specified. The volume of fluid shall not be less than 20 times that of the specimens. After immersion, the specimens shall be lightly wiped and air dried for 30 to 60 minutes at standard conditions.

TEST FLUIDS FOR FLUID RESISTANCE

| Fluid | Specification |
|---------------------------------|---------------|
| Hydraulic fluid, petroleum base | MIL- PRF-5606 |
| JP-4 Fuel | MIL-DTL-5624 |
| Lubricating oil | MIL-PRF-7808 |
| Lubricating oil | MIL-PRF-23699 |
| Deicing fluid | SAE-AMS1424 |

PERFORMANCE:

Temperature life

Three straight and three 90° angle boots of each material (Type A and Type B) shall be installed on a connector and exposed to rated temperature (Type A: 150°C) (Type B: 200°C) for 1000 hours. At the end of this time they shall be cooled to room temperature and the pull-off tests shown on figure 5 shall be performed. The minimum force required to pull boot from connector at any angle shall be 25 pounds.




FIGURE 5. Pull off test method.

Acceptance Tests.


Acceptance tests shall consist of dimensional recovery, tensile strength, elongation, stiffness, heat shock, and hardness.

TABLE I. Material requirements, heat shrinkable boots.

| | | | To the total string to the | |
|---------------------------------------|-----------|--------------------------|--|--------------------------------|
| Material Property | Unit | Requirement Type A | Requirement Type B | Method of Test |
| PHYSICAL | inches | In accordance with | In accordance with | ASTM-D876 |
| Dimensions | | figures 3 and 4 | figures 3 and 4 | |
| Dimensional Recovery | | | | |
| Elastic Memory | percent | 275 min expansion | 200 min expansion | See qualification requirements |
| | | 93 min retraction | 90 min expansion | |
| Tensile Strength | psi | 1200 minimum | 1800 minimum | ASTM-D412 |
| Ultimate Elongation | percent | 250 minimum | 300 minimum | Die D |
| Specific Gravity | | 1.40 maximum | 1.95 maximum | ASTM-D792 |
| Low Temperature | | No cracking | No cracking | See qualification requirements |
| Flexibility at 55°C (67°F) | | | | |
| Heat Shock (4 hours) | | No dripping, flowing | No dripping, flowing | |
| Type A 225°C (437°F) | | or cracking | or cracking | See qualification requirements |
| Type B 300°C (572°F) | | | | |
| Heat Aging (168 hours) | | | | |
| Type A 175°C | | | | See qualification requirements |
| Type B 250°C | | | | |
| Followed by tests for | | | | |
| Tensile Strength Elongation | | 1000 minimum | 1200 minimum | ASTM-D412, |
| | percent | 200 minimum | 250 minimum | Die D |
| Hardness | Shore D | 38 ± 5 | 85 ± 5 | ASTM-D2240 |
| Stiffness | psi | 10000 maximum | 7500 maximum | ASTM-D747 |
| CHEMICAL | | Nonburning | nonburning | ASTM-D635 |
| Flammability | | | | |
| Fungus Resistance | | Rating or 1 or less | Rating of 1 or less | ASTM-D876 |
| Corrosion 16 hrs at 175°C | | Noncorrosive | noncorrosive | ASTM-D2671 |
| Copper Mirror | | | | Appendix A 1. 5. 1 |
| | | | | |
| Fluid Resistance | | | | |
| 24 hrs at 25°C | | | | |
| Hydraulic fluid | | | | See qualification requirements |
| JP 4 fuel | | | | |
| Lubricating Oil | | | | |
| Dejeje a Hujd | | | | |
| Deicing fluid Followed by test for | | | | |
| | : | 750 maining : : : : | 4000 | |
| Tensile Strength | psi | 750 minimum | 1600 minimum | |
| Elongation | percent | 200 minimum | 200 minimum | ACTM DOZC |
| Matar Abaaratian | noroont | 0 E maximum | 0.5 maximum | ASTM-D876 |
| Water Absorption | percent | 0.5 maximum | 0.5 maximum | Procedure A |
| ELECTRICAL | volts/mil | 200 minimum | 200 minimum | ASTM-D876 |
| Dielectric Strength | | - | _ | |
| Volume Resistivity | ohms cm | 10 ¹² minimum | 10 ¹⁰ minimum | ASTM-D257 |
| , | 1 | | | 1 |

Part or Identifying Number (PIN): The PIN shall consist of the military designation, specification sheet number, boot configuration, backshell size, and component designation.

PIN Example:



Component designation:

A: Polyolefin (150°C) - boot and backshell

B: Fluoroelastomer (200°C) - boot and backshell

(M: Backshell only

(A: Polyolefin boot only

(B: Fluoroelastomer boot only

Additional PIN examples:

M83723/16M22(M - Metal backshell for shell size 22. M82723/16A22(B -Right angle fluoroelastomer boot to fit backshell size 22.

Amendment notations. The margins of this specification are marked with vertical lines to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notation.

Referenced documents. In addition to MIL-DTL-83723, this document references the following:

MIL-DTL-5624 MIL-PRF-5606 MIL-PRF-7808 MIL-PRF-23699 ASTM-D257 ASTM-D412 ASTM-D635 ASTM-D747 ASTM-D792 ASTM-D876 ASTM-D2240 ASTM-D2671 SAE-AMS1424

Air Force - 99

CONCLUDING MATERIAL

(Project 5935-2010-087)

Custodians:

Air Force – 85

DLA - CC

Review activity:

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.daps.dla.mil.