

https://www.phoenixcontact.com/us/products/0800298



Please be informed that the data shown in this PDF document is generated from our online catalog. Please find the complete data in the user documentation. Our general terms of use for downloads are valid.



Shrink sleeve, Roll, white, unmarked, can be labeled with: THERMOMARK E.300 (D)/600 (D), THERMOMARK ROLLMASTER 300/600, THERMOMARK ROLL X1, THERMOMARK ROLL, THERMOMARK ROLL 2.0, THERMOMARK W, THERMOMARK X1.2, cable diameter range: 12.7 ... 38.1 mm, unperforated, mounting type: slide-on, Number of individual labels: 1, roll length: 15 m, text field height: 60 mm, text field width: 15000 mm

Product description

The continuous shrink sleeves in the WMS... product family can be assembled to create individual marker lengths using the THERMOMARK E. CUTTER or E.CUTTER/P. After the printing, assembly, and applying process, you have the option of shrinking the marked shrink sleeves by applying heat manually and thus fixing them on the cable/wire.

Your advantages

- · Permanent and captive identification of single-core wires, wires, cables, pneumatic hoses, and other cylindrical objects
- High flexibility, as individual marker lengths ranging from 3.45 mm ... 2000 mm (0.14" ... 78.7") can be realized in combination with the cutter and perforation cutter
- As an option, the sleeves can be shrunk by applying heat manually to fix the sleeve in position
- High diameter coverage with a shrink ratio of 3:1
- · Widely used and proven worldwide in control cabinet and machine building, the oil and gas industry, and the railway industry

Commercial data

Item number	0800298
Packing unit	1 pc
Minimum order quantity	1 pc
Note	Made to order (non-returnable)
Sales key	BG14
Product key	BG2216
GTIN	4046356625876
Weight per piece (including packing)	880.3 g
Weight per piece (excluding packing)	832.1 g
Customs tariff number	39173200
Country of origin	CN



https://www.phoenixcontact.com/us/products/0800298



Technical data

Notes

Note on application	For the THERMOMARK ROLL and THERMOMARK ROLL 2.0 roll printers, this material can only be processed with an external media hub.
Material information	The specified minimum wire diameter of the shrink sleeve refers to its use as a marking material and does not guarantee any insulation characteristics once shrunk.
	Depending on the processed material batch, as well as the storage and processing conditions, the maximum insertable wire diameter may be reduced.

Product properties

Product type	Shrink sleeve
Marking	
Number of individual labels	1
Identification technology	Thermal transfer for rolls

Dimensions

Height	63.7 mm
Length of roll	15000.00 mm
External dimensions	
Outside diameter	12.7 mm 38.1 mm

Text field

Text field width	15000 mm
Text field height	60 mm

Material specifications

Color	white (RAL 9010)
Material	Polyolefine
Base element material	polyolefine
Shrink rate	3:1
Components	halogen-free
Shrink temperature	> 85 °C

Cable/line

Environmental and real-life conditions

Test for substances that would hinder coating with paint or varnish

Result	Test passed
Test for substances that would hinder coating with paint or varnish	



https://www.phoenixcontact.com/us/products/0800298



Result	Test passed
Scratch test for the determining scratch resistance	EN 100 4540 4 0000 (f III - 1 - 1 - 1
Specification	EN ISO 1518-1:2023 (following)
Requirements	≥ 5 N
Result	Test passed
resafilm test	
Specification	DIN EN ISO 2409:2020-12 (following)
Result	Test passed
JV resistance	
Specification	DIN EN ISO 4892-2:2021-11 (following)
Result	Test passed
Test duration	96 h
Temperature resistance	ANSI/III 060 2049.02 (fallaccina)
Specification Test duration	ANSI/UL 969-2018:03 (following) 240 h
Test duration	
Rating 125 °C (150 °C)	Test passed
Vipe resistance of inscriptions	
Specification	DIN EN 61010-1 (VDE 0411-01):2020-03
	DIN EN 62208 (VDE 0660-511):2012-06 (in parts)
Isopropyl [CAS No. 67-63-0]	Test passed
n-Hexane [CAS No. 110-54-3]	Test passed
Water + Petroleum ether [CAS No. 64742-82-1]	Test passed
Sodium hydroxide 0.1 mol/l [CAS No. 1310-73-2]	Test passed
Ethanol (99 %) [CAS No. 64-17-5]	Test passed
Acetone (99 %) [CAS No. 67-64-1]	Test passed
Specification	ISO 175:2010 (following)
Test duration	168 h
Sodium hydroxide 0.1 mol/l [CAS No. 1310-73-2]	Test passed
Ethanol (99 %) [CAS No. 64-17-5]	Test passed
Acetone (99 %) [CAS No. 67-64-1]	Test passed
Diesel [CAS No. 68476-34-6]	Test passed
IRM 901	Test passed
IRM 902	Test passed

Testing in a condensation changing climate in the presence of sulfur dioxide



0800298

https://www.phoenixcontact.com/us/products/0800298

Specification	EN ISO 22479:2022-06
Result	Test passed
Procedure	Method B
Cycles	2
Salt spray test	
Specification	DIN EN IEC 60068-2-11 (VDE 0468-2-11):2022-10
Result	Test passed
Test duration	96 h
Ambient conditions Ambient temperature (operation)	-55 °C 125 °C
Recommended ambient temperature (storage/transport)	23 °C
Recommended humidity (storage/transport)	50 % (Storage in a dry and dark place in the original packaging i recommended)
Shelf life	5 years
andards and regulations	
Wipe resistance	DIN EN 61010-1 (VDE 0411-1)
ounting	
Mounting type	slide-on



0800298

https://www.phoenixcontact.com/us/products/0800298

Approvals

🌣 To download certificates, visit the product detail page: https://www.phoenixcontact.com/us/products/0800298



CSA

Approval ID: 252259



cULus Recognized

Approval ID: E310982_Vol2_Sec1



0800298

https://www.phoenixcontact.com/us/products/0800298

Classifications

UNSPSC 21.0

ECLASS

ECLASS-13.0	27281102
ECLASS-15.0	27281102
ETIM	
ETIM 9.0	EC001530
UNSPSC	

39131500

E	ТІМ	
	ETIM 9.0	EC001530
UI	NSPSC	



0800298

https://www.phoenixcontact.com/us/products/0800298

Environmental product compliance

EU RoHS

Fulfills EU RoHS substance requirements	Yes, No exemptions
EU REACH SVHC	

Phoenix Contact 2025 © - all rights reserved https://www.phoenixcontact.com

Phoenix Contact USA 586 Fulling Mill Road Middletown, PA 17057, United States (+717) 944-1300 info@phoenixcon.com